

# **Bassic**®

## **Standard flexible polyurethane**



The **BASIC**® group of flexible foams covers a wide range of densities and properties for application in different sectors, such as upholstered furniture, seating, rest, packaging, insulation, etc.

Having been subjected to rigorous quality control testing in relation to their physical-mechanical properties, **BASIC**® foams comply with high quality standards for the different products that they are applied to. For that purpose, the raw materials used are certified and endorsed by trustworthy suppliers, and there is also monitoring through laboratory tests of all the manufactured goods.

This, along with experience in the sector and the production of flexible PU, as well as the philosophy of comprehensive service and personalised customer service, has earned us the trust of many clients in both national and international markets.



	DENSITY (kg/m <sup>3</sup> )	CFD (kPa)	ILD 40% (N)	RESILIENCE (%)
<b>ZE SW</b>	20 +/- 5%	1	45	52
<b>ZH BG</b>	25 ± 5%	3,25	150	50
<b>ZH B</b>	25 +/- 5%	3,75	170	46
<b>ZH</b>	25 +/- 5%	4,75	200	43
<b>ZI BG</b>	28 +/- 5%	3,25	150	53
<b>ZI B</b>	28 +/- 5%	3,75	175	50
<b>ZI</b>	28 +/- 5%	4,75	190	45
<b>ZI XD VERDE</b>	28 ± 5%	6,5	260	45
<b>ZJ CN</b>	30 +/- 5%	4	180	53
<b>ZJ C</b>	30 +/- 5%	4	180	53
<b>ZJ</b>	30 +/- 5%	5,25	230	45
<b>ZJ XD</b>	30 ± 5%	7,5	290	45
<b>ZJ PR</b>	30 ± 5%	9	345	45